

ASME B36.10M-2015

[Revision of ASME B36.10M-2004 (R2010)]

Welded and Seamless Wrought Steel Pipe

KCM Special Steel Co.,Ltd

Web: <https://www.duplexstainlesssteelpipes.com>

E-mail: kcmspecialsteel@outlook.com

AN AMERICAN NATIONAL STANDARD



ASME B36.10M-2015

[Revision of ASME B36.10M-2004 (R2010)]

Welded and Seamless Wrought Steel Pipe

AN AMERICAN NATIONAL STANDARD



**The American Society of
Mechanical Engineers**

Two Park Avenue • New York, NY • 10016 USA

Date of Issuance: August 31, 2015

This Standard will be revised when the Society approves the issuance of a new edition.

Periodically certain actions of the ASME B32 Committee may be published as Cases. Cases are published on the ASME Web site under the B32 Committee Page at go.asme.org/B32committee as they are issued.

Errata to codes and standards may be posted on the ASME Web site under the Committee Pages to provide corrections to incorrectly published items, or to correct typographical or grammatical errors in codes and standards. Such errata shall be used on the date posted.

The B32 Committee Page can be found at go.asme.org/B32committee. There is an option available to automatically receive an e-mail notification when errata are posted to a particular code or standard. This option can be found on the appropriate Committee Page after selecting "Errata" in the "Publication Information" section.

ASME is the registered trademark of the American Society of Mechanical Engineers.

This code or standard was developed under procedures accredited as meeting the criteria for American National Standards. The Consensus Committee that approved the code or standard was balanced to assure that individuals from competent and concerned interests have had an opportunity to participate. The proposed code or standard was made available for public review and comment that provides an opportunity for additional public input from industry, academia, regulatory agencies, and the public-at-large.

ASME does not "approve," "rate," or "endorse" any item, construction, proprietary device, or activity.

ASME does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a standard against liability for infringement of any applicable letters patent, nor assume any such liability. Users of a code or standard are expressly advised that the determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representative(s) or person(s) affiliated with industry is not to be interpreted as government or industry endorsement of this code or standard.

ASME accepts responsibility for only those interpretations of this document issued in accordance with the established ASME procedures and policies, which precludes the issuance of interpretations by individuals.

No part of this document may be reproduced in any form,
in an electronic retrieval system or otherwise,
without the prior written permission of the publisher.

The American Society of Mechanical Engineers
Two Park Avenue, New York, NY 10016-5990

Copyright © 2015 by
THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS
All rights reserved
Printed in U.S.A.

CONTENTS

[illegible]

FOREWORD

[illegible]

)v)b 8)))COMH 8)) ;

x)s AI))))ITNPAn))))) 8
)))))))))))))))
))))))f un)x)Nq))Nq Ay)))))
))))))f)x)ji)I8ITNA
 y))))))ITOTAf))))))))))
))) 8))))))))))))
 y)J)))))) Af))))))))))
))))))))y)JAn))f un)x)Nq))
)))) 8)))f un)x))))y)LAy
))))))))))f)s)x)
 k)L8ITPFA
 k))))))))ITPNf))))))
)))))f un)))))y)J Ay)L8i))
))))n)u 8)))) 8))))))
 Ay)))))))))))f
 s)x))o)N8ITPNA
 y)))))ITPS)))xn)) Ay)))))
)))))))))))))JNAAt
))))IO A))))) 8))))IO A
))))))FA) A)))))))
 FAI) Ay)))))xn)))))y)J Af))
))xn)))) 8)))) 8)xn)))))
)))))Nay)xn))))))))))
 y)J Ay)))))))))))f
 s)x))o)IS8ITPTA
 k)))))ITSM Ay)f s xn) 8))))) 8
))y)I8))))))))))f xyr)
 f un) Af))))))))))f un)
)))y)J Ay))))))f)s)x))f
 IT8ITNA
 y))))))))))))f
 s)x)n))f)J8ITINA
 y)ITIO))))y)J8)) 8))))
)) 8))))))))))i s 8)
)f un)x)) Ay)ITIO))))f)s)x)
)x)JL8ITIOA
 y)JFFF)))))y)J))))))) 9
)))N Ay)I))))))))x)I8J8L8
 N8S8)T)) Ay)JFFF)))))f)s)x))
 i)I8JFFFA
 y)JFFM)))))N)y)IAn)))))
)))An)))))i s)))y)IAy))
)))f)s)x))o)JL8JFFMA
 y)JFIN))))y)I)))s)AL5)) Ay
 JFIN))))f)s)x))o)IC8JFINA

ASME B32 COMMITTEE

Metal and Metal Alloy

Wrought Mill Product Nominal Sizes

(The following is the roster of the Committee at the time of approval of this Standard.)

OFFICERS

J. A. Gruber, *Chair*
A. R. Amaral, *Secretary*

COMMITTEE PERSONNEL

A. R. Amaral, The American Society of Mechanical Engineers
D. O. Bankston, Jr., Consultant
D. Friken, Becht Engineering Co.
J. A. Gruber, J A Gruber & Associates
R. A. McLeod, General Electric Co.
M. L. Nayyara, NICE
A. P. Rangus, Bechtel
R. Reamy, Turner Industries Group
M. H. Skinningberg, Consultant
F. W. Tatar, FM Global

CORRESPONDENCE WITH THE B32 COMMITTEE

k B e w q i) w))))))))))
))) B e) :)))) w))))) g
)))) g :))) g)) B g))
) T

w :f I Gw)g
x)e)w))q)i
x)t)e
r) :r)FEFFASSE
TCC B B Cm

t)v Bv))))))w)))
)))) :)))))))
))w Be))))) B
x)g))))))w Bw)))
))) :))) 3 5)) :))
))))) :))) B
t))g Bg)))))))))
:))))))))) :))
)))))) Bg)))))

e wq i))))))))) e wq i) g))) B
 v)) g)))) w)) r)) f) m Bx)
))) w)))) :) :)) 3 5)))))
 u)) v))))))) g Bv)) g)))
))) 3 5)) w)))) g)) g B
 v)))))))))))))))) g
)))) :))))))))))) B
 e wq i)))))))))))))))))
)))))))))))))))))
)))))))))))))))))
 : : : : : : : : B
 e) g)) q Bx) f IGw) g))))) C
)))))))))))))))))
 C)))))))) w))) f IGw) g Bf
 g)))))))))))) g) t)
 B B Cf IG B

INTENTIONALLY LEFT BLANK

WELDED AND SEAMLESS WROUGHT STEEL PIPE

1 SCOPE

[illegible]

2 SIZE

y)))))))
) A
y)))) s ux))))) s ux) EF
3hs) GDD9 9))))))
) t A A))))
))))) t A A)))) :
))))))))))
) t A A))))) A
e))))))))))
)))) t A A))))
)))) t A A))))
A
y)))) s ux) EI 3hs) GDD9)
)))))) t A A)))
) A

3 MATERIALS

y))))
)))) e xyr) A

4 WALLTHICKNESS

y))))))y)EA

5 WEIGHTS

y))))))) :
))))))) EA
 y)))))) 9))) 9
)))))) T

p EDAS3 4

[illegible]

p)))) (DAE))
)))) EN A3 DNA 4
))))) (EAD))
))))) EN A3 DNA
43) W))))) t A A
))))) 4
))) 9))) :
p) (DAE)))) 9
)) :)) (DAE) B
p

6 PERMISSIBLE VARIATIONS

$$\begin{array}{ccccccc} & &) &) & &) &) \\ &) &) & &) &) &) \\) &) &) & & \text{Au} &) & : \\ &) &) &) &) &) & A \end{array}$$

7 PIPE THREADS

z)) 9)))
))) e s x r B e x r i f E F D E u) y 9
 l) u) n 4 A
 x) M) E D)))
))) e s x r B e x r i f E F D E A

8 WALL THICKNESS DESIGNATIONS

i y))) x 9
:)x 9)h)i :x)))
))) Ae
))k 9)x)s
)))))))

)) Bz))z)MD)
)))u wz)ED4k u)IND) Bg)))
 z))) B4VBL) 5)) B
 l A))z)ID))))
 u wz)T4k u)I DD59) Bg)))
 l A))) B4EI BD 5)) B
 w)))))))))
 z 9l A 9)k)l A 9
 z)u))))g wpz
 N Bp))))))z
 u))))) B

9 WALL THICKNESS SELECTION

))))))) A
))))))))
 9)))))))
))))))))
) 9))))))g zt l)h
)w)))i 9g zt l)hLEi))w)
 w 9))) 9)))
 Bg))))) 1/2)E
))))))))
)))) B

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
		0.049		...				1.24	
1/8	0.405	0.057	0.19	...	10	6(3)	10.3	1.45	0.28
1/8	0.405	0.068	0.21	STD	30	6(3)	10.3	1.73	0.32
1/8	0.405	0.095	0.24	XS	40	6(3)	10.3	2.41	0.37
1/8	0.405		0.31		80	6(3)	10.3		0.47
		0.065		...				1.65	
1/4	0.540	0.073	0.33	...	10	8(3)	13.7	1.85	0.49
1/4	0.540	0.088	0.36	STD	30	8(3)	13.7	2.24	0.54
1/4	0.540	0.119	0.43	XS	40	8(3)	13.7	3.02	0.63
1/4	0.540		0.54		80	8(3)	13.7		0.80
		0.065		...				1.65	
3/8	0.675	0.073	0.42	...	10	10	17.1	1.85	0.63
3/8	0.675	0.091	0.47	STD	30	10	17.1	2.31	0.70
3/8	0.675	0.126	0.57	XS	40	10	17.1	3.20	0.84
3/8	0.675		0.74		80	10	17.1		1.10
		0.065		...				1.65	
	0.840	0.083	0.54	...	5	15	21.3	2.11	0.80
1/2	0.840	0.095	0.67	...	10	15	21.3	2.41	1.00
1/2	0.840	0.109	0.76	STD	30	15	21.3	2.77	1.12
1/2	0.840		0.85		40	15	21.3		1.27
1/2	0.840	0.147	0.85	XS	40	15	21.3	3.73	
		0.065		...				1.65	
	0.840	0.188	1.09	...	80	15	21.3	4.78	1.62
1/2	0.840	0.294	1.31	XXS	160	15	21.3	7.47	1.95
1/2	0.840		1.72		.	15	21.3		2.55
1/2		0.065		...				1.65	
	1.050	0.083	0.69	...	5	20	26.7	2.11	1.03
3/4	1.050	0.095	0.86	...	10	20	26.7	2.41	1.28
3/4	1.050	0.113	0.97	STD	30	20	26.7	2.87	1.44
3/4	1.050		1.13		40	20	26.7		1.69
3/4	1.050	0.154	1.13	XS	40	20	26.7	3.91	
		0.065		...				1.65	
	1.050	0.219	1.48	...	80	20	26.7	5.56	2.20
3/4	1.050	0.308	1.95	XXS	160	20	26.7	7.82	2.90
3/4	1.050		2.44		.	20	26.7		3.64
3/4		0.065		...				1.65	
	1.315	0.109	0.87	...	5	25	33.4	2.77	1.29
1	1.315	0.114	1.41	...	10	25	33.4	2.90	2.09
1	1.315	0.133	1.46	STD	30	25	33.4	3.38	2.18
1	1.315		1.68		40	25	33.4		2.50
1	1.315	0.179	1.68	XS	40	25	33.4	4.55	
		0.065		...				1.65	
	1.315	0.250	2.17	...	80	25	33.4	6.35	3.24
1	1.315	0.358	2.85	XXS	160	25	33.4	9.09	4.24
1	1.315		3.66		.	25	33.4		5.45
1		0.065		...				1.65	
	1.660	0.109	1.11	...	5	32	42.2	2.77	1.65
	1.660	0.117	1.81	...	10	32	42.2	2.97	2.69
1 1/4	1.660	0.140	1.93	STD	30	32	42.2	3.56	2.87
1 1/4	1.660		2.27		40	32	42.2		3.39
1 1/4	1.660	0.191	2.27	XS	40	32	42.2	4.85	
		0.065		...				1.65	
	1.660	0.250	3.00	...	80	32	42.2	6.35	4.47
1 1/4	1.660	0.382	3.77	XXS	160	32	42.2	9.70	5.61
1 1/4	1.660		5.22		.	32	42.2		7.77
1 1/4		0.065		...				1.65	
	1.900	0.109	1.28	...	5	40	48.3	2.77	1.90
1 1/4	1.900	0.125	2.09	...	10	40	48.3	3.18	3.11
1 1/2	1.900	0.145	2.37	STD	30	40	48.3	3.68	3.53
1 1/2	1.900		2.72		40	40	48.3		4.05
1 1/2	1.900	0.200	2.72	XS	40	40	48.3	5.08	
		0.065		...				1.65	
	1.900	0.281	3.63	...	80	40	48.3	7.14	5.41
1 1/2	1.900	0.400	4.86	XXS	160	40	48.3	10.15	7.25
1 1/2	1.900		6.41		.	40	48.3		9.55
1 1/2		0.065		...				1.65	
1 1/2		0.065		...				1.65	
1 1/2		0.065		...				1.65	

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
2		0.065		...				1.65	
2	2.375	0.083	1.61	...	5	50	60.3	2.11	2.39
2	2.375	0.109	2.03	...	...	50	60.3	2.77	3.03
2	2.375	0.125	2.64	...	10	50	60.3	3.18	3.93
2	2.375		3.01	...	30	50	60.3		4.48
2		0.141		...				3.58	
2	2.375	0.154	3.37	STD	...	50	60.3	3.91	5.01
2	2.375	0.172	3.66	...	40	50	60.3	4.37	5.44
2	2.375	0.188	4.05	...	...	50	60.3	4.78	6.03
2	2.375	0.218	4.40	XS	...	50	60.3	5.54	6.54
2	2.375	0.250	5.03	...	80	50	60.3	6.35	7.48
2	2.375	0.281	5.68	...	...	50	60.3	7.14	8.45
2	2.375	0.344	6.29	...	...	50	60.3	8.74	9.36
2	2.375	0.436	7.47	XXS	160	50	60.3	11.07	11.11
1	2.375		9.04	...	...	50	60.3		13.44
		0.083		...				2.11	
2 1/2	2.875	0.109	2.48	...	5	65	73.0	2.77	3.69
2 1/2	2.875	0.120	3.22	...	...	65	73.0	3.05	4.80
2 1/2	2.875	0.125	3.53	...	10	65	73.0	3.18	5.26
2 1/2	2.875		3.67	...	...	65	73.0	3.58	5.48
2 1/2	2.875	0.141		...	...	65	73.0	3.96	6.13
2 1/2	2.875	0.156	4.12	...	...	65	73.0	4.37	6.74
2 1/2	2.875	0.172	4.53	...	...	65	73.0	4.78	7.40
2 1/2	2.875	0.188	4.97	...	...	65	73.0	5.16	8.04
2 1/2	2.875	0.203	5.40	STD	30	65	73.0	5.49	8.63
2 1/2	2.875	0.216	5.80	...	40	65	73.0	6.35	9.14
2 1/2	2.875	0.250	6.14	...	...	65	73.0	7.01	10.44
2 1/2	2.875	0.276	7.02	XS	...	65	73.0	9.53	11.41
2 1/2	2.875	0.375	7.67	...	80	65	73.0	14.02	14.92
2 1/2	2.875	0.552	10.02	XXS	160	65	73.0	20.39	20.39
2 1/2	2.875	0.083	13.71	...	...	65	73.0	2.11	2.39
2 1/2	3.500	0.109	3.03	...	5	80	88.9	2.77	4.52
3	3.500	0.120	3.95	...	...	80	88.9	3.05	5.88
3	3.500	0.125	4.34	...	10	80	88.9	3.18	6.46
3	3.500	0.141	4.51	...	...	80	88.9	3.58	6.72
3	3.500	0.156	5.06	...	...	80	88.9	3.96	7.53
3	3.500	0.172	5.58	...	...	80	88.9	4.37	8.30
3	3.500	0.188	6.12	...	...	80	88.9	4.78	9.11
3	3.500	0.216	6.66	STD	30	80	88.9	5.49	9.92
3	3.500		7.58	...	40	80	88.9		11.29
3									
3									
3	3.500	0.250	8.69	...	...	80	88.9	6.35	12.93
3	3.500	0.281	9.67	...	...	80	88.9	7.14	14.40
3	3.500	0.300	10.26	XS	80	80	88.9	7.62	15.27
3	3.500	0.438	14.34	...	160	80	88.9	11.13	21.35
3	3.500	0.600	18.60	XXS	...	80	88.9	15.24	27.68
3 1/2	4.000	0.083	3.48	...	5	90	101.6	2.11	5.18
3 1/2	4.000	0.109	4.53	...	...	90	101.6	2.77	6.75
3 1/2	4.000	0.120	4.98	...	10	90	101.6	3.05	7.41
3 1/2	4.000	0.125	5.18	...	...	90	101.6	3.18	7.72
3 1/2	4.000	0.141	5.82	...	...	90	101.6	3.58	8.65
3 1/2	4.000	0.156	6.41	...	...	90	101.6	3.96	9.54
3 1/2	4.000	0.172	7.04	...	...	90	101.6	4.37	10.48
3 1/2	4.000	0.188	7.66	...	30	90	101.6	4.78	11.41

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
1		0.226		STD				5.74	
3/2	4.000	0.250	9.12	...	40	90	101.6	6.35	13.57
3/2	4.000	0.281	10.02	...	...	90	101.6	7.14	14.92
3/2	4.000	0.318	11.17	XS	...	90	101.6	8.08	16.63
3/2	4.000		12.52		80	90	101.6		18.64
		0.083		...				2.11	
4	4.500	0.109	3.92	...	5	100	114.3	2.77	5.84
4	4.500	0.120	5.12	...	...	100	114.3	3.05	7.62
4	4.500	0.125	5.62	...	10	100	114.3	3.18	8.37
4	4.500	0.141	5.85	...	...	100	114.3	3.58	8.71
4	4.500	0.156	6.57	...	...	100	114.3	3.96	9.78
4	4.500	0.172	7.24	...	...	100	114.3	4.37	10.78
4	4.500	0.188	7.96	...	...	100	114.3	4.78	11.85
4	4.500	0.203	8.67	...	30	100	114.3	5.16	12.91
4	4.500	0.219	9.32	...	.	100	114.3	5.56	13.89
4	4.500	0.237	10.02	STD	...	100	114.3	6.02	14.91
4	4.500	0.250	10.80	...	40	100	114.3	6.35	16.08
4	4.500	0.281	11.36	...	.	100	114.3	7.14	16.91
4	4.500	0.312	12.67	...	...	100	114.3	7.92	18.87
4	4.500	0.337	13.97	XS	...	100	114.3	8.56	20.78
4	4.500	0.438	15.00	...	80	100	114.3	11.13	22.32
4	4.500	0.531	19.02	...	120	100	114.3	13.49	28.32
4	4.500	0.674	22.53	XXS	160	100	114.3	17.12	33.54
4	4.500	0.083	27.57	...	.	100	114.3	2.11	41.03
5	5.563	0.109	4.86	...	...	125	141.3	2.77	7.24
5	5.563	0.125	6.36	...	5	125	141.3	3.18	9.46
5	5.563	0.134	7.27	...	.	125	141.3	3.40	10.83
5	5.563	0.156	7.78	...	10	125	141.3	3.96	11.56
5	5.563	0.188	9.02	...	...	125	141.3	4.78	13.41
5	5.563	0.219	10.80	...	.	125	141.3	5.56	16.09
5	5.563	0.258	12.51	STD	...	125	141.3	6.55	18.61
5	5.563		14.63		40	125	141.3		21.77
					...				
5	5.563	0.281	15.87	...	...	125	141.3	7.14	23.62
5	5.563	0.312	17.51	...	...	125	141.3	7.92	26.05
5	5.563	0.344	19.19	...	...	125	141.3	8.74	28.57
5	5.563	0.375	20.80	XS	80	125	141.3	9.53	30.97
5	5.563	0.500	27.06	...	120	125	141.3	12.70	40.28
5	5.563	0.625	32.99	...	160	125	141.3	15.88	49.12
5	5.563	0.750	38.59	XXS	...	125	141.3	19.05	57.43
6	6.625	0.083	5.80	...	...	150	168.3	2.11	8.65
6	6.625	0.109	7.59	...	5	150	168.3	2.77	11.31
6	6.625	0.125	8.69	...	...	150	168.3	3.18	12.95
6	6.625	0.134	9.30	...	10	150	168.3	3.40	13.83
6	6.625	0.141	9.77	...	.	150	168.3	3.58	14.54
6	6.625	0.156	10.79	...	...	150	168.3	3.96	16.05
6	6.625	0.172	11.87	...	...	150	168.3	4.37	17.67
6	6.625	0.188	12.94	...	...	150	168.3	4.78	19.28
6	6.625	0.203	13.94	...	...	150	168.3	5.16	20.76
6	6.625	0.219	15.00	...	...	150	168.3	5.56	22.31
6	6.625	0.250	17.04	...	...	150	168.3	6.35	25.36
6	6.625	0.280	18.99	STD	40	150	168.3	7.11	28.26

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
6		0.312		...				7.92	
6	6.625	0.344	21.06	...	...	150	168.3	8.74	31.33
6	6.625	0.375	23.10	...	...	150	168.3	9.53	34.39
6	6.625	0.432	25.05	XS	...	150	168.3	10.97	37.31
6	6.625		28.60	...	8 0	150	168.3		42.56
6		0.500		...				12.70	
6	6.625	0.562	32.74	...	...	150	168.3	14.27	48.73
6	6.625	0.625	36.43	...	120	150	168.3	15.88	54.21
6	6.625		40.09	...	...	150	168.3		59.69
6		0.719		...				18.26	
6	6.625	0.750	45.39	...	1 6 0	150	168.3	19.05	67.57
6	6.625	0.864	47.10	XXS	...	150	168.3	21.95	70.12
6	6.625	0.875	53.21	...	...	150	168.3	22.23	79.22
8	6.625	0.109	53.78	...	...	150	168.3	2.77	80.08
8	8.625	0.125	9.92	...	5	200	219.1	3.18	14.78
8	8.625	0.148	11.36	...	.	200	219.1	3.76	16.93
8	8.625	0.156	13.41	...	10	200	219.1	3.96	19.97
8	8.625		14.12	...	.	200	219.1		21.01
8	8.625	0.188		...	.	200	219.1	4.78	
8	8.625	0.203	16.96	...	.	200	219.1	5.16	25.26
8	8.625	0.219	18.28	...	.	200	219.1	5.56	27.22
8	8.625	0.250	19.68	...	.	200	219.1	6.35	29.28
8	8.625		22.38	...	20	200	219.1	7.04	33.32
8	8.625	0.277		...	.	200	219.1		
8	8.625	0.312	24.72	...	30	200	219.1	7.92	36.82
8	8.625	0.322	27.73	STD	.	200	219.1	8.18	41.25
8	8.625	0.344	28.58	...	40	200	219.1	8.74	42.55
8	8.625		30.45	...	.	200	219.1		45.34
8	8.625	0.375		...	.	200	219.1	9.53	
8	8.625	0.406	33.07	...	...	200	219.1	10.31	49.25
8	8.625	0.438	35.67	...	60	200	219.1	11.13	53.09
8	8.625	0.500	38.33	XS	.	200	219.1	12.70	57.08
8	8.625		43.43	...	80	200	219.1		64.64
8	8.625	0.562		...	.	200	219.1	14.27	
8	8.625	0.594	48.44	...	.	200	219.1	15.09	72.08
8	8.625	0.625	51.00	...	100	200	219.1	15.88	75.92
8	8.625	0.719	53.45	...	...	200	219.1	18.26	79.59
8	8.625		60.77	...	120	200	219.1		90.44
8	8.625	0.750		...	.	200	219.1	19.05	
8	8.625	0.812	63.14	...	...	200	219.1	20.62	93.98
8	8.625	0.875	67.82	XXS	140	200	219.1	22.23	100.93
8	8.625	0.906	72.49	...	...	200	219.1	23.01	107.93
8	8.625		74.76	...	160	200	219.1		111.27
8	8.625	1.000		...	...	200	219.1	25.40	121.33
10		0.134		...				3.40	
10	10.750	0.156	15.21	...	5	250	273.0	3.96	22.61
10	10.750	0.165	17.67	...	...	250	273.0	4.19	26.27
10	10.750	0.188	18.67	...	10	250	273.0	4.78	27.78
10	10.750		21.23	...	...	250	273.0		31.62
10	10.750	0.203		...	.	250	273.0	5.16	
10	10.750	0.219	22.89	...	.	250	273.0	5.56	34.08
10	10.750	0.250	24.65	...	...	250	273.0	6.35	36.67
10	10.750		28.06	...	20	250	273.0		41.76
10	10.750	0.279		...	.	250	273.0	7.09	
10	10.750		31.23	...	...	250	273.0		46.49
10	10.750	0.307		...	.	250	273.0	7.80	
10	10.750	0.344	34.27	...	30	250	273.0	8.74	51.01
10	10.750	0.365	38.27	STD	...	250	273.0	9.27	56.96
10	10.750	0.438	40.52	...	40	250	273.0	11.13	60.29
10	10.750		48.28	...	.	250	273.0		71.88

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
10	10.750	0.500		XS				12.70	
10	10.750	0.562	54.79	...	60	250	273.0	14.27	81.53
10	10.750	0.594	61.21	...	...	250	273.0	15.09	91.05
10	10.750	0.625	64.49	...	80	250	273.0	15.88	95.98
			67.65	...	...	250	273.0		100.69
10	10.750	0.719		...				18.26	
10	10.750	0.812	77.10	...	100	250	273.0	20.62	114.71
10	10.750	0.844	86.26	...	...	250	273.0	21.44	128.34
10	10.750	0.875	89.38	...	120	250	273.0	22.23	133.01
10	10.750	0.938	92.37	...	...	250	273.0	23.83	137.48
10	10.750	1.000	98.39	XXS	...	250	273.0	25.40	146.43
10	10.750	1.125	104.23	...	140	250	273.0	28.58	155.10
10	10.750	1.250	115.75	...	160	250	273.0	31.75	172.27
			126.94	...	...	250	273.0		188.90
12	12.750	0.156		...	5	300	323.8	3.96	
12	12.750	0.172	21.00	...	...			4.37	31.24
12	12.750	0.180	23.13	...	...	300	323.8	4.57	34.43
12	12.750	0.188	24.19	...	10	300	323.8	4.78	35.98
12	12.750	0.203	25.25	...	...	300	323.8	5.16	37.61
12	12.750	0.219	27.23	...	...	300	323.8	5.56	40.55
12	12.750	0.250	29.34	...	...	300	323.8	6.35	43.64
12	12.750	0.281	33.41	...	20	300	323.8	7.14	49.71
12	12.750	0.312	37.46	...	...	300	323.8	7.92	55.76
12	12.750	0.330	41.48	...	...	300	323.8	8.38	61.70
12	12.750	0.344	43.81	...	30	300	323.8	8.74	65.19
12	12.750	0.375	45.62	STD	...	300	323.8	9.53	67.91
12	12.750	0.406	49.61	...	...	300	323.8	10.31	73.86
12	12.750	0.438	53.57	...	40	300	323.8	11.13	79.71
12	12.750	0.500	57.65	XS	...	300	323.8	12.70	85.82
12	12.750	0.562	65.48	...	...	300	323.8	14.27	97.44
12	12.750	0.625	73.22	...	60	300	323.8	15.88	108.93
12	12.750	0.688	81.01	...	...	300	323.8	17.48	120.59
12	12.750	0.750	88.71	...	80	300	323.8	19.05	132.05
12	12.750	0.812	96.21	...	...	300	323.8	20.62	143.17
12	12.750	0.844	103.63	...	...	300	323.8	21.44	154.17
12	12.750	0.875	107.42	...	100	300	323.8	22.23	159.87
12	12.750	0.938	111.08	...	...	300	323.8	23.83	165.33
12	12.750	1.000	118.44	XXS	...	300	323.8	25.40	176.29
12	12.750	1.062	125.61	...	120	300	323.8	26.97	186.92
12	12.750	1.125	132.69	...	...	300	323.8	28.58	197.43
12	12.750	1.250	139.81	...	140	300	323.8	31.75	208.08
12	12.750	1.312	153.67	...	...	300	323.8	33.32	228.68
			160.42	...	160	300	323.8		238.69
14	14.000	0.156		...	5	350	355.6	3.96	
14	14.000	0.188	23.09	...	...			4.78	34.34
14	14.000	0.203	27.76	...	...	350	355.6	5.16	41.36
14	14.000	0.210	29.94	...	...	350	355.6	5.33	44.59
14	14.000	0.219	30.96	...	...	350	355.6	5.56	46.04
14	14.000	0.250	32.26	...	...	350	355.6	6.35	48.00
14	14.000	0.281	36.75	...	10	350	355.6	7.14	54.69
14	14.000	0.312	41.21	...	...	350	355.6	7.92	61.36
			45.65	...	20	350	355.6		67.91

..

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
14	14.000	0.344		...				8.74	
14	14.000	0.375	50.22	STD	...	350	355.6	9.53	74.76
14	14.000	0.406	54.62	...	30	350	355.6	10.31	81.33
14	14.000	0.438	59.00	...	...	350	355.6	11.13	87.79
			63.50	...	40	350	355.6		94.55
14	14.000	0.469		...				11.91	
14	14.000	0.500	67.84	XS	...	350	355.6	12.70	100.95
14	14.000	0.562	72.16	...	...	350	355.6	14.27	107.40
14	14.000	0.594	80.73	...	...	350	355.6	15.09	120.12
14	14.000	0.625	85.13	...	60	350	355.6	15.88	126.72
14	14.000	0.688	89.36	...	.	350	355.6	17.48	133.04
14	14.000	0.750	97.91	...	.	350	355.6	19.05	145.76
14	14.000	0.812	106.23	...	80	350	355.6	20.62	158.11
			114.48	...	...	350	355.6		170.34
14	14.000	0.875	122.77	...	...	350	355.6	22.23	182.76
14	14.000	0.938	130.98	...	100	350	355.6	23.83	194.98
14	14.000	1.000	138.97	...	...	350	355.6	25.40	206.84
14	14.000	1.062	146.88	...	...	350	355.6	26.97	218.58
14	14.000	1.094	150.93	...	120	350	355.6	27.79	224.66
14	14.000	1.125	154.84	...	...	350	355.6	28.58	230.49
14	14.000	1.250	170.37	...	140	350	355.6	31.75	253.58
14	14.000	1.406	189.29	...	160	350	355.6	35.71	281.72
14	14.000	2.000	256.56	...	.	350	355.6	50.80	381.85
14	14.000	2.125	269.76	...	...	350	355.6	53.98	401.52
14	14.000	2.200	277.51	...	...	350	355.6	55.88	413.04
14	14.000	2.500	307.34	...	...	350	355.6	63.50	457.43
16	16.000	0.165	27.93	...	...	400	406.4	4.19	41.56
16	16.000	0.188	31.78	...	.	400	406.4	4.78	47.34
16	16.000	0.203	34.28	...	...	400	406.4	5.16	51.06
16	16.000	0.219	36.95	...	...	400	406.4	5.56	54.96
16	16.000	0.250	42.09	...	10	400	406.4	6.35	62.65
16	16.000	0.281	47.22	...	.	400	406.4	7.14	70.30
16	16.000	0.312	52.32	...	20	400	406.4	7.92	77.83
16	16.000	0.344	57.57	...	.	400	406.4	8.74	85.71
16	16.000	0.375	62.64	STD	30	400	406.4	9.53	93.27
16	16.000	0.406	67.68	...	.	400	406.4	10.31	100.71
16	16.000	0.438	72.86	...	...	400	406.4	11.13	108.49
16	16.000	0.469	77.87	...	...	400	406.4	11.91	115.87
16	16.000	0.500	82.85	XS	40	400	406.4	12.70	123.31
16	16.000	0.562	92.75	...	.	400	406.4	14.27	138.00
16	16.000	0.625	102.72	...	.	400	406.4	15.88	152.94
16	16.000	0.656	107.60	...	60	400	406.4	16.66	160.13
16	16.000	0.688	112.62	...	...	400	406.4	17.48	167.66
16	16.000	0.750	122.27	...	.	400	406.4	19.05	181.98
16	16.000	0.812	131.84	...	...	400	406.4	20.62	196.18
16	16.000	0.844	136.74	...	80	400	406.4	21.44	203.54
16	16.000	0.875	141.48	...	...	400	406.4	22.23	210.61
16	16.000	0.938	151.03	...	.	400	406.4	23.83	224.83
16	16.000	1.000	160.35	...	.	400	406.4	25.40	238.66
16	16.000	1.031	164.98	...	100	400	406.4	26.19	245.57
				...	...				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
16	16.000	1.062		...			26.97		252.37
16	16.000	1.125	169.59	...	...	400	406.4	28.58	266.30
16	16.000	1.188	178.89	...	...	400	406.4	30.18	280.01
16	16.000	1.219	188.11	...	...	400	406.4	30.96	286.66
			192.61	...	1 2 0	400	406.4		
16	16.000	1.250		...				31.75	293.35
16	16.000	1.438	197.10	...	...	400	406.4	36.53	333.21
16	16.000	1.594	223.85	...	140	400	406.4	40.49	365.38
			245.48	...	160	400	406.4		
18	18.000	0.165		...				4.19	46.79
18	18.000	0.188	31.46	...	5	450	457	4.78	53.31
18	18.000	0.219	35.80	...	...	450	457	5.56	61.90
18	18.000	0.250	41.63	...	...	450	457	6.35	70.57
18	18.000	0.281	47.44	...	10	450	457	7.14	79.21
18	18.000	0.312	53.23	...	.	450	457	7.92	87.71
18	18.000	0.344	58.99	...	20	450	457	8.74	96.62
18	18.000	0.375	64.93	STD	...	450	457	9.53	105.17
18	18.000	0.406	70.65	...	...	450	457	10.31	113.58
18	18.000	0.438	76.36	...	...	450	457	11.13	122.38
18	18.000	0.469	82.23	...	30	450	457	11.91	130.73
18	18.000	0.500	87.89	XS	.	450	457	12.70	139.16
18	18.000	0.562	93.54	...	...	450	457	14.27	155.81
18	18.000	0.625	104.76	...	40	450	457	15.88	172.75
18	18.000	0.688	116.09	...	.	450	457	17.48	189.47
18	18.000	0.750	127.32	...	...	450	457	19.05	205.75
18	18.000	0.812	138.30	...	60	450	457	20.62	221.91
18	18.000	0.875	149.20	...	.	450	457	22.23	238.35
18	18.000	0.938	160.18	...	.	450	457	23.83	254.57
18	18.000	1.000	171.08	...	80	450	457	25.40	270.36
18	18.000	1.062	181.73	...	...	450	457	26.97	286.02
18	18.000	1.125	192.29	...	...	450	457	28.58	301.96
18	18.000	1.156	202.94	...	...	450	457	29.36	309.64
18	18.000	1.188	208.15	...	100	450	457	30.18	317.68
18	18.000	1.250	213.51	...	...	450	457	31.75	332.97
18	18.000	1.375	223.82	...	.	450	457	34.93	363.58
18	18.000	1.562	244.37	...	120	450	457	39.67	408.28
18	18.000	1.781	274.48	...	140	450	457	45.24	459.39
20	20.000	0.188	308.79	...	160	450	457		
20	20.000	0.219	39.82	...	5	500	508	4.78	59.32
20	20.000	0.250	46.31	...	.	500	508	5.56	68.89
20	20.000	0.281	52.78	...	10	500	508	6.35	78.56
20	20.000	0.312	59.23	...	...	500	508	7.14	88.19
20	20.000	0.344	65.66	...	.	500	508	7.92	97.68
20	20.000	0.375	72.28	STD	...	500	508	8.74	107.61
20	20.000	0.406	78.67	...	20	500	508	9.53	117.15
20	20.000	0.438	85.04	...	...	500	508	10.31	126.54
20	20.000	0.469	91.59	...	...	500	508	11.13	136.38
20	20.000	0.500	97.92	XS	.	500	508	11.91	145.71
20	20.000	0.562	104.23	...	30	500	508	12.70	155.13
			116.78	...	...	500	508	14.27	173.75
				...	...				
				...	...				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
20	20.000	0.594		...				15.09	183.43
20	20.000	0.625	123.23	...	40	500	508	15.88	192.73
20	20.000	0.688	129.45	...	...	500	508	17.48	211.45
20	20.000	0.750	142.03	...	...	500	508	19.05	229.71
			154.34	...	...	500	508		
20	20.000	0.812		...				20.62	247.84
20	20.000	0.875	166.56	...	60	500	508	22.23	266.31
20	20.000	0.938	178.89	...	...	500	508	23.83	284.54
20	20.000	1.000	191.14	...	...	500	508	25.40	302.30
20	20.000	1.031	203.11	...	...	500	508	26.19	311.19
20	20.000	1.062	209.06	...	80	500	508	26.97	319.94
20	20.000	1.125	215.00	...	...	500	508	28.58	337.91
20	20.000	1.188	227.00	...	...	500	508	30.18	355.63
20	20.000	1.250	238.91	...	...	500	508	31.75	372.91
20	20.000	1.281	250.55	...	...	500	508	32.54	381.55
20	20.000	1.312	256.34	...	100	500	508	33.32	390.05
20	20.000	1.375	262.10	...	...	500	508	34.93	407.51
20	20.000	1.500	273.76	...	...	500	508	38.10	441.52
20	20.000	1.750	296.65	...	120	500	508	44.45	508.15
20	20.000	1.969	341.41	...	140	500	508	50.01	564.85
			379.53	...	160	500	508		
22	22.000	0.188		...				4.78	65.33
22	22.000	0.219	43.84	...	5	550	559	5.56	75.89
22	22.000	0.250	50.99	...	...	550	559	6.35	86.55
22	22.000	0.281	58.13	...	10	550	559	7.14	97.17
22	22.000	0.312	65.24	...	...	550	559	7.92	107.64
22	22.000	0.344	72.34	...	...	550	559	8.74	118.60
22	22.000	0.375	79.64	STD	...	550	559	9.53	129.14
22	22.000	0.406	86.69	...	20	550	559	10.31	139.51
			93.72	...	...	550	559		
22	22.000	0.438	100.96	...	...	550	559	11.13	150.38
22	22.000	0.469	107.95	...	...	550	559	11.91	160.69
22	22.000	0.500	114.92	XS	...	550	559	12.70	171.10
22	22.000	0.562	128.79	...	30	550	559	14.27	191.70
22	22.000	0.625	142.81	...	...	550	559	15.88	212.70
22	22.000	0.688	156.74	...	...	550	559	17.48	233.44
22	22.000	0.750	170.37	...	...	550	559	19.05	253.67
22	22.000	0.812	183.92	...	...	550	559	20.62	273.78
22	22.000	0.875	197.60	...	...	550	559	22.23	294.27
22	22.000	0.938	211.19	...	60	550	559	23.83	314.51
22	22.000	1.000	224.49	...	...	550	559	25.40	334.25
22	22.000	1.062	237.70	...	...	550	559	26.97	353.86
22	22.000	1.125	251.05	...	...	550	559	28.58	373.85
				...	80	550	559		
22	22.000	1.188	264.31	...	...	550	559	30.18	393.59
22	22.000	1.250	277.27	...	...	550	559	31.75	412.84
22	22.000	1.312	290.15	...	...	550	559	33.32	431.96
22	22.000	1.375	303.16	...	...	550	559	34.93	451.45
22	22.000	1.438	316.08	...	100	550	559	36.53	470.69
				...	...	550	559		
22	22.000	1.500	328.72	...	...	550	559	38.10	489.44
22	22.000	1.625	353.94	...	...	550	559	41.28	527.05
22	22.000	1.875	403.38	...	120	550	559	47.63	600.67
22	22.000	2.125	451.49	...	140	550	559	53.98	672.30
				...	160	550	559		

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
24	24.000	0.218	...	...	...	...	610	5.54	...
24	24.000	0.250	55.42	...	5	600	610	6.35	82.58
24	24.000	0.281	63.47	...	10	600	610	7.14	94.53
24	24.000	0.312	71.25	...	...	600	610	7.92	106.15
24	24.000	0.344	79.01	...	...	600	610	8.74	117.60
24	24.000	0.375	86.99	STD	...	600	610	9.53	129.60
24	24.000	0.406	94.71	...	20	600	610	10.31	141.12
24	24.000	0.438	102.40	...	...	600	610	11.13	152.48
24	24.000	0.469	110.32	...	...	600	610	11.91	164.38
24	24.000	0.500	117.98	XS	...	600	610	12.70	175.67
24	24.000	0.562	125.61	...	...	600	610	14.27	187.07
24	24.000	0.625	140.81	...	30	600	610	15.88	209.65
24	24.000	0.688	156.17	...	...	600	610	17.48	232.67
24	24.000	0.750	171.45	...	40	600	610	19.05	255.43
24	24.000	0.812	186.41	...	...	600	610	20.62	277.63
24	24.000	0.875	201.28	...	...	600	610	22.23	299.71
24	24.000	0.938	216.31	...	...	600	610	23.83	322.23
24	24.000	0.969	231.25	...	...	600	610	24.61	344.48
24	24.000	1.000	238.57	...	60	600	610	25.40	355.28
24	24.000	1.062	245.87	...	...	600	610	26.97	366.19
24	24.000	1.125	260.41	...	...	600	610	28.58	387.79
24	24.000	1.188	275.10	...	...	600	610	30.18	409.80
24	24.000	1.219	289.71	...	...	600	610	30.96	431.55
24	24.000	1.250	296.86	...	80	600	610	31.75	442.11
24	24.000	1.312	304.00	...	...	600	610	33.32	452.77
24	24.000	1.375	318.21	...	...	600	610	34.93	473.87
24	24.000	1.438	332.56	...	...	600	610	36.53	495.38
24	24.000	1.500	346.83	...	...	600	610	38.10	516.63
24	24.000	1.531	360.79	...	...	600	610	38.89	537.36
24	24.000	1.562	367.74	...	100	600	610	39.67	547.74
24	24.000	1.812	374.66	...	...	600	610	46.02	557.97
24	24.000	2.062	429.79	...	120	600	610	52.37	640.07
24	24.000	2.344	483.57	...	140	600	610	59.54	720.19
24	24.000	2.344	542.64	...	160	600	610	...	808.27
26	26.000	0.250	...	...	...	...	660	6.35	...
26	26.000	0.281	68.82	...	...	650	660	7.14	102.36
26	26.000	0.312	77.26	...	...	650	660	7.92	114.96
26	26.000	0.344	85.68	...	10	650	660	8.74	127.36
26	26.000	0.375	94.35	STD	...	650	660	9.53	140.37
26	26.000	0.406	102.72	...	...	650	660	10.31	152.88
26	26.000	0.438	111.08	...	...	650	660	11.13	165.19
26	26.000	0.469	119.69	...	...	650	660	11.91	178.10
26	26.000	0.500	128.00	XS	...	650	660	12.70	190.36
26	26.000	0.562	136.30	...	20	650	660	14.27	202.74
26	26.000	0.625	152.83	...	...	650	660	15.88	227.25
26	26.000	0.688	169.54	...	...	650	660	17.48	252.25
26	26.000	0.750	186.16	...	...	650	660	19.05	276.98
26	26.000	0.812	202.44	...	...	650	660	20.62	301.12
26	26.000	0.875	218.64	...	...	650	660	22.23	325.14
26	26.000	0.938	235.01	...	...	650	660	23.83	349.64
26	26.000	1.000	251.30	...	...	650	660	25.40	373.87
26	26.000	1.000	267.25	...	...	650	660	...	397.51
				...	...				
				...	...				
				...	...				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
28	28.000	0.250		...				6.35	110.35
28	28.000	0.281	74.16	...	...	700	711	7.14	123.94
28	28.000	0.312	83.26	...	...	700	711	7.92	137.32
28	28.000	0.344	92.35	...	10	700	711	8.74	151.37
			101.70	...	...	700	711		
28	28.000	0.375		STD	...			9.53	164.86
28	28.000	0.406	110.74	...	...	700	711	10.31	178.16
28	28.000	0.438	119.76	...	...	700	711	11.13	192.10
28	28.000	0.469	129.05	...	...	700	711	11.91	205.34
28	28.000	0.500	138.03	XS	...	700	711	12.70	218.71
28	28.000	0.562	146.99	...	20	700	711	14.27	245.19
28	28.000	0.625	164.84	...	.	700	711	15.88	272.23
28	28.000	0.688	182.90	...	30	700	711	17.48	298.96
28	28.000	0.750	200.87	...	.	700	711	19.05	325.08
28	28.000	0.812	218.48	...	.	700	711	20.62	351.07
28	28.000	0.875	236.00	...	.	700	711	22.23	377.60
28	28.000	0.938	253.72	...	.	700	711	23.83	403.84
28	28.000	1.000	271.36	...	.	700	711	25.40	429.46
			288.63	...	.	700	711		
30	30.000	0.250		...				6.35	118.34
30	30.000	0.281	79.51	...	5	750	762	7.14	132.92
30	30.000	0.312	89.27	...	.	750	762	7.92	147.29
30	30.000	0.344	99.02	...	10	750	762	8.74	162.36
30	30.000	0.375	109.06	STD	.	750	762	9.53	176.85
30	30.000	0.406	118.76	...	.	750	762	10.31	191.12
30	30.000	0.438	128.44	...	.	750	762	11.13	206.10
30	30.000	0.469	138.42	...	.	750	762	11.91	220.32
30	30.000	0.500	148.06	XS	.	750	762	12.70	234.68
30	30.000	0.562	157.68	...	20	750	762	14.27	263.14
30	30.000	0.625	176.86	...	.	750	762	15.88	292.20
30	30.000	0.688	196.26	...	30	750	762	17.48	320.95
30	30.000	0.750	215.58	...	.	750	762	19.05	349.04
30	30.000	0.812	234.51	...	.	750	762	20.62	377.01
30	30.000	0.875	253.36	...	.	750	762	22.23	405.56
30	30.000	0.938	272.43	...	.	750	762	23.83	433.81
30	30.000	1.000	291.41	...	.	750	762	25.40	461.41
30	30.000	1.062	310.01	...	.	750	762	26.97	488.88
30	30.000	1.125	328.53	...	.	750	762	28.58	516.93
30	30.000	1.188	347.26	...	.	750	762	30.18	544.68
30	30.000	1.250	365.90	...	.	750	762	31.75	571.79
			384.17	...	.	750	762		
32	32.000	0.250		...				6.35	126.32
32	32.000	0.281	84.85	...	.	800	813	7.14	141.90
32	32.000	0.312	95.28	...	.	800	813	7.92	157.25
32	32.000	0.344	105.69	...	10	800	813	8.74	173.35
32	32.000	0.375	116.41	STD	.	800	813	9.53	188.83
32	32.000	0.406	126.78	...	.	800	813	10.31	204.09
32	32.000	0.438	137.12	...	.	800	813	11.13	220.10
32	32.000	0.469	147.78	...	.	800	813	11.91	235.29
32	32.000	0.500	158.08	XS	.	800	813	12.70	250.65
32	32.000	0.562	168.37	...	20	800	813	14.27	281.09
32	32.000	0.625	188.87	...	.	800	813	15.88	312.17
32	32.000	0.688	209.62	...	30	800	813	17.48	342.94
			230.29	...	40	800	813		
				...	.				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
32	32.000	0.750		...				19.05	373.60
32	32.000	0.812	250.55	...	...	800	813	20.62	402.94
32	32.000	0.875	270.72	...	...	800	813	22.23	433.52
32	32.000	0.938	291.14	...	...	800	813	23.83	463.78
			311.47	...	...	800	813		
32	32.000	1.000		...				25.40	493.35
32	32.000	1.062	331.39	...	...	800	813	26.97	522.80
32	32.000	1.125	351.23	...	...	800	813	28.58	552.88
32	32.000	1.188	371.31	...	...	800	813	30.18	582.64
32	32.000	1.250	391.30	...	...	800	813	31.75	611.72
			410.90	...	...	800	813		
34	34.000	0.250		...				6.35	134.31
34	34.000	0.281	90.20	...	...	850	864	7.14	150.88
34	34.000	0.312	101.29	...	...	850	864	7.92	167.21
34	34.000	0.344	112.36	...	10	850	864	8.74	184.34
34	34.000	0.375	123.77	STD	...	850	864	9.53	200.82
34	34.000	0.406	134.79	...	...	850	864	10.31	217.06
34	34.000	0.438	145.80	...	...	850	864	11.13	234.10
34	34.000	0.469	157.14	...	...	850	864	11.91	250.27
34	34.000	0.500	168.11	XS	...	850	864	12.70	266.63
34	34.000	0.562	179.06	...	20	850	864	14.27	299.04
34	34.000	0.625	200.89	...	...	850	864	15.88	332.14
34	34.000	0.688	222.99	...	30	850	864	17.48	364.92
34	34.000	0.750	245.00	...	40	850	864	19.05	396.96
34	34.000	0.812	266.58	...	...	850	864	20.62	428.88
34	34.000	0.875	288.08	...	...	850	864	22.23	461.48
34	34.000	0.938	309.84	...	...	850	864	23.83	493.75
34	34.000	1.000	331.52	...	...	850	864	25.40	525.30
34	34.000	1.062	352.77	...	...	850	864	26.97	556.73
34	34.000	1.125	373.94	...	...	850	864	28.58	588.83
34	34.000	1.188	395.36	...	...	850	864	30.18	620.60
34	34.000	1.250	416.70	...	...	850	864	31.75	651.65
			437.62	...	...	850	864		
36	36.000	0.250		...				6.35	142.14
36	36.000	0.281	95.54	...	...	900	914	7.14	159.68
36	36.000	0.312	107.30	...	...	900	914	7.92	176.97
36	36.000	0.344	119.03	...	10	900	914	8.74	195.12
36	36.000	0.375	131.12	STD	...	900	914	9.53	212.57
36	36.000	0.406	142.81	...	...	900	914	10.31	229.77
36	36.000	0.438	154.48	...	...	900	914	11.13	247.82
36	36.000	0.469	166.51	...	...	900	914	11.91	264.96
36	36.000	0.500	178.14	XS	...	900	914	12.70	282.29
36	36.000	0.562	189.75	...	20	900	914	14.27	316.63
36	36.000	0.625	212.90	...	...	900	914	15.88	351.73
36	36.000	0.688	236.35	...	30	900	914	17.48	386.47
36	36.000	0.750	259.71	...	...	900	914	19.05	420.45
36	36.000	0.812	282.62	...	40	900	914	20.62	454.30
36	36.000	0.875	305.44	...	...	900	914	22.23	488.89
36	36.000	0.938	328.55	...	...	900	914	23.83	523.14
			351.57	...	...	900	914		

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
36	36.000	1.000		...					
36	36.000	1.062	374.15	...	..	900	914	25.40	556.62
36	36.000	1.125	396.64	...	.	900	914	26.97	589.98
36	36.000	1.188	419.42	...	..	900	914	28.58	624.07
36	36.000	1.250	442.10	...	.	900	914	30.18	657.81
			464.35	...	..	900	914	31.75	690.80
38	38.000	0.312		...	.			7.92	186.94
38	38.000	0.344	125.70	...	..	950	965	8.74	206.11
38	38.000	0.375	138.47	STD	.	950	965	9.53	224.56
38	38.000	0.406	150.83	...	..	950	965	10.31	242.74
38	38.000	0.438	163.16	...	.	950	965	11.13	261.82
38	38.000	0.469	175.87	...	..	950	965	11.91	279.94
38	38.000	0.500	188.17	XS	.	950	965	12.70	298.26
38	38.000	0.562	200.44	...	..	950	965	14.27	334.58
38	38.000	0.625	224.92	...	.	950	965	15.88	371.70
38	38.000	0.688	249.71	...	..	950	965	17.48	408.46
38	38.000	0.750	274.42	...	..	950	965	19.05	444.41
38	38.000	0.812	298.65	...	.	950	965	20.62	480.24
38	38.000	0.875	322.80	...	..	950	965	22.23	516.85
38	38.000	0.938	347.26	...	..	950	965	23.83	553.11
38	38.000	1.000	371.63	...	..	950	965	25.40	588.57
38	38.000	1.062	395.53	...	.	950	965	26.97	623.90
38	38.000	1.125	419.35	...	..	950	965	28.58	660.01
38	38.000	1.188	443.47	...	..	950	965	30.18	695.77
38	38.000	1.250	467.50	...	..	950	965	31.75	730.74
			491.07	...	.	950	965		
40	40.000	0.312		...	.			7.92	196.90
40	40.000	0.344	132.37	...	..	1000	1016	8.74	217.11
40	40.000	0.375	145.83	STD	..	1000	1016	9.53	236.54
40	40.000	0.406	158.85	...	..	1000	1016	10.31	255.71
40	40.000	0.438	171.84	...	.	1000	1016	11.13	275.82
40	40.000	0.469	185.24	...	..	1000	1016	11.91	294.92
40	40.000	0.500	198.19	XS	..	1000	1016	12.70	314.23
40	40.000	0.562	211.13	...	..	1000	1016	14.27	352.53
40	40.000	0.625	236.93	...	.	1000	1016	15.88	391.67
40	40.000	0.688	263.07	...	..	1000	1016	17.48	430.45
40	40.000	0.750	289.13	...	..	1000	1016	19.05	468.37
40	40.000	0.812	314.69	...	..	1000	1016	20.62	506.17
40	40.000	0.875	340.16	...	.	1000	1016	22.23	544.81
40	40.000	0.938	365.97	...	..	1000	1016	23.83	583.08
40	40.000	1.000	391.68	...	..	1000	1016	25.40	620.51
40	40.000	1.062	416.91	...	..	1000	1016	26.97	657.82
40	40.000	1.125	442.05	...	.	1000	1016	28.58	695.96
40	40.000	1.188	467.52	...	..	1000	1016	30.18	733.73</

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
42	42.000	0.469		...				11.91	309.90
42	42.000	0.500	208.22	XS	..	1050	1067	12.70	330.21
42	42.000	0.562	221.82	...	.	1050	1067	14.27	370.48
42	42.000	0.625	248.95	...	..	1050	1067	15.88	411.64
			276.44		.	1050	1067		
42	42.000	0.688		...	..			17.48	452.43
42	42.000	0.750	303.84	...	.	1050	1067	19.05	492.33
42	42.000	0.812	330.72	...	..	1050	1067	20.62	532.11
42	42.000	0.875	357.52	...	.	1050	1067	22.23	572.77
42	42.000	0.938	384.67	...		1050	1067		
42	42.000	1.000	411.74	...	..	1050	1067	23.83	613.05
42	42.000	1.062	438.29	...				25.40	652.46
42	42.000	1.125	464.76	...	.	1050	1067	26.97	691.75
42	42.000	1.188	491.57	...	..	1050	1067	28.58	731.91
42	42.000	1.250	518.30	...	..	1050	1067	30.18	771.69
			544.52		..	1050	1067	31.75	810.60
44	44.000	0.344		...	.			8.74	239.09
44	44.000	0.375	160.54	STD	..	1100	1118	9.53	260.52
44	44.000	0.406	174.88	...	..	1100	1118	10.31	281.64
44	44.000	0.438	189.20	...		1100	1118	11.13	303.82
44	44.000	0.469	203.97	...	.	1100	1118	11.91	324.88
44	44.000	0.500	218.25	XS	..	1100	1118	12.70	346.18
44	44.000	0.562	232.51	...	..	1100	1118	14.27	388.42
44	44.000	0.625	260.97	...	..	1100	1118	15.88	431.62
44	44.000	0.688	289.80	...	.	1100	1118	17.48	474.42
44	44.000	0.750	318.55	...	..	1100	1118	19.05	516.29
44	44.000	0.812	346.76	...	..	1100	1118	20.62	558.04
44	44.000	0.875	374.88	...		1100	1118	22.23	600.73
44	44.000	0.938	403.38	...	.	1100	1118	23.83	643.03
			431.79		..	1100	1118		
44	44.000	1.000		...	..			25.40	684.41
44	44.000	1.062	459.67	...	..	1100	1118	26.97	725.67
44	44.000	1.125	487.47	...	..	1100	1118	28.58	767.85
44	44.000	1.188	515.63	...	.	1100	1118	30.18	809.65
44	44.000	1.250	543.70	...	.	1100	1118	31.75	850.54
			571.25		..	1100	1118		
46	46.000	0.344		...	..			8.74	249.87
46	46.000	0.375	167.89	STD	..	1150	1168	9.53	272.27
46	46.000	0.406	182.90	...	.	1150	1168	10.31	294.35
46	46.000	0.438	197.88	...	..	1150	1168	11.13	317.54
46	46.000	0.469	213.33	...	.	1150	1168	11.91	339.56
46	46.000	0.500	228.27	XS	..	1150	1168	12.70	361.84
46	46.000	0.562	243.20	...		1150	1168	14.27	406.02
46	46.000	0.625	272.98	...	..	1150	1168	15.88	451.20
46	46.000	0.688	303.16	...	..	1150	1168	17.48	495.97
46	46.000	0.750	333.26	...	..	1150	1168	19.05	539.78
46	46.000	0.812	362.79	...	.	1150	1168	20.62	583.47
46	46.000	0.875	392.24	...	..	1150	1168	22.23	628.14
46	46.000	0.938	422.09	...	.	1150	1168	23.83	672.41
			451.85		..	1150	1168		
46	46.000	1.000		...				25.40	715.73
46	46.000	1.062	481.05	...	.	1150	1168	26.97	758.92
46	46.000	1.125	510.17	...	..	1150	1168	28.58	803.09
46	46.000	1.188	539.68	...	..	1150	1168	30.18	846.86
46	46.000	1.250	569.10	...	..	1150	1168	31.75	889.69
			597.97		.				
					..				
					..				
					.				
					..				
					.				
					..				
					..				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	PlainEnd Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
48	48.000	0.344		...				8.74	260.86
48	48.000	0.375	175.25	STD	..	1200	1219	9.53	284.25
48	48.000	0.406	190.92	...	.	1200	1219	10.31	307.32
48	48.000	0.438	206.56	...	..	1200	1219	11.13	331.54
			222.70		.	1200	1219		
48	48.000	0.469		...				11.91	354.54
48	48.000	0.500	238.30	XS	..	1200	1219	12.70	377.81
48	48.000	0.562	253.89	...	.	1200	1219	14.27	423.97
48	48.000	0.625	285.00	...	..	1200	1219	15.88	471.17
48	48.000	0.688	316.52	...	.	1200	1219	17.48	517.95
48	48.000	0.750	347.97	...	..	1200	1219	19.05	563.74
48	48.000	0.812	378.83	...		1200	1219	20.62	609.40
48	48.000	0.875	409.61	...	.	1200	1219	22.23	656.10
48	48.000	0.938	440.80	...	..	1200	1219	23.83	702.38
			471.90		..	1200	1219		
48	48.000	1.000		...				25.40	747.67
48	48.000	1.062	502.43	...	.	1200	1219	26.97	792.84
48	48.000	1.125	532.88	...	..	1200	1219	28.58	839.04
48	48.000	1.188	563.73	...		1200	1219	30.18	884.82
48	48.000	1.250	594.50	...	..	1200	1219	31.75	929.62
			624.70			1200	1219		
52	52.000	0.375		...	.			9.53	308.23
52	52.000	0.406	206.95	...	..	1300	1321	10.31	333.26
52	52.000	0.438	223.93	...	.	1300	1321	11.13	359.54
52	52.000	0.469	241.42	...	..	1300	1321	11.91	384.50
52	52.000	0.500	258.36	...	.	1300	1321	12.70	409.76
52	52.000	0.562	275.27	...	..	1300	1321	14.27	459.86
52	52.000	0.625	309.03	...	..	1300	1321	15.88	511.12
52	52.000	0.688	343.25	...		1300	1321	17.48	561.93
			377.39		.	1300	1321		
52	52.000	0.750		...		1300	1321	19.05	611.66
52	52.000	0.812	410.90	...	..	1300	1321	20.62	661.27
52	52.000	0.875	444.33	...		1300	1321	22.23	712.02
52	52.000	0.938	478.21	...	.	1300	1321	23.83	762.33
52	52.000	1.000	512.01	...	..	1300	1321	25.40	811.57
52	52.000	1.062	545.19	...	..	1300	1321	26.97	860.69
52	52.000	1.125	578.29	...	.	1300	1321	28.58	910.93
52	52.000	1.188	611.84	...	..	1300	1321	30.18	960.74
52	52.000	1.250	645.30	...	..	1300	1321	31.75	1 009.49
			678.15		..	1300	1321		
56	56.000	0.375		...				9.53	331.96
56	56.000	0.406	222.99	...	.	1400	1422	10.31	358.94
56	56.000	0.438	241.29	...	..	1400	1422	11.13	387.26
56	56.000	0.469	260.15	...		1400	1422	11.91	414.17
56	56.000	0.500	278.41	...	.	1400	1422	12.70	441.39
56	56.000	0.562	296.65	...	..	1400	1422	14.27	495.41
56	56.000	0.625	333.06	...	..	1400	1422	15.88	550.67
56	56.000	0.688	369.97	...		1400	1422	17.48	605.46
56	56.000	0.750	406.80	...	.	1400	1422	19.05	659.11
56	56.000	0.812	442.97	...	..	1400	1422	20.62	712.63
56	56.000	0.875	479.05	...	..	1400	1422	22.23	767.39
56	56.000	0.938	515.63	...		1400	1422	23.83	821.68
			552.12		.	1400	1422		
					..				
					..				
					.				
					..				
					..				
					.				
					..				
					..				
					.				
					..				
					..				

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
56	56.000	1.000		...				25.40	874.83
56	56.000	1.062	587.95	...	..	1400	1422	26.97	927.86
56	56.000	1.125	623.70	...	..	1400	1422	28.58	982.12
56	56.000	1.188	659.94	...	..	1400	1422	30.18	1 035.91
56	56.000	1.250	696.10	...	..	1400	1422	31.75	1 088.57
			731.60	...	..	1400	1422		
60	60.000	0.375		...	..	1500		9.53	355.94
60	60.000	0.406	239.02	...	..	1500	1524	10.31	384.87
60	60.000	0.438	258.65	...	..	1500	1524	11.13	415.26
60	60.000	0.469	278.88	...	..	1500	1524	11.91	444.13
60	60.000	0.500	298.47	...	..	1500	1524	12.70	473.34
60	60.000	0.562	318.03	...	..	1500	1524	14.27	531.30
60	60.000	0.625	357.09	...	..	1500	1524	15.88	590.62
60	60.000	0.688	396.70	...	..	1500	1524	17.48	649.44
60	60.000	0.750	436.22	...	..	1500	1524	19.05	707.03
60	60.000	0.812	475.04	...	..	1500	1524	20.62	764.50
60	60.000	0.875	513.77	...	..	1500	1524	22.23	823.31
60	60.000	0.938	553.04	...	..	1500	1524	23.83	881.63
60	60.000	1.000	592.23	...	..	1500	1524	25.40	938.73
60	60.000	1.062	630.71	...	..	1500	1524	26.97	995.71
60	60.000	1.125	669.11	...	..	1500	1524	28.58	1 054.01
60	60.000	1.188	708.05	...	..	1500	1524	30.18	1 111.83
60	60.000	1.250	746.90	...	..	1500	1524	31.75	1 168.44
			785.05	...	..	1500	1524		
64	64.000	0.375		...	..	1600		9.53	379.91
64	64.000	0.406	255.06	...	..	1600	1626	10.31	410.81
64	64.000	0.438	276.01	...	..	1600	1626	11.13	443.25
64	64.000	0.469	297.61	...	..	1600	1626	11.91	474.09
64	64.000	0.500	318.52	...	..	1600	1626	12.70	505.29
64	64.000	0.562	339.41	...	..	1600	1626	14.27	567.20
64	64.000	0.625	381.12	...	..	1600	1626	15.88	630.56
64	64.000	0.688	423.42	...	..	1600	1626	17.48	693.41
64	64.000	0.750	465.64	...	..	1600	1626	19.05	754.95
64	64.000	0.812	507.11	...	..	1600	1626	20.62	816.37
64	64.000	0.875	548.49	...	..	1600	1626	22.23	879.23
64	64.000	0.938	590.46	...	..	1600	1626	23.83	941.57
64	64.000	1.000	632.34	...	..	1600	1626	25.40	1 002.62
64	64.000	1.062	673.47	...	..	1600	1626	26.97	1 063.55
64	64.000	1.125	714.52	...	..	1600	1626	28.58	1 125.90
64	64.000	1.188	756.15	...	..	1600	1626	30.18	1 187.74
64	64.000	1.250	797.69	...	..	1600	1626	31.75	1 248.30
			838.50	...	..	1600	1626		
68	68.000	0.469		...	..	1700		11.91	503.75
68	68.000	0.500	338.57	...	..	1700	1727	12.70	536.92
68	68.000	0.562	360.79	...	..	1700	1727	14.27	602.74
68	68.000	0.625	405.15	...	..	1700	1727	15.88	670.12
68	68.000	0.688	450.15	...	..	1700	1727	17.48	736.95
68	68.000	0.750	495.06	...	..	1700	1727	19.05	802.40
68	68.000	0.812	539.18	...	..	1700	1727	20.62	867.73
68	68.000	0.875	583.21	...	..	1700	1727	22.23	934.60
68	68.000	0.938	627.87	...	..	1700	1727	23.83	1 000.92
			672.45	...	..	1700	1727		

Table 1 Dimensions and Weights of Welded and Seamless Wrought Steel Pipe (Cont'd)

NPS [Note (1)]	Customary Units			Identification [Standard (STD), Extra-Strong (XS), or Double Extra Strong (XXS)]	Schedule No.	DN [Note (2)]	SI Units		
	Outside Diameter, in.	Wall Thickness, in.	Plain End Weight, lb/ft				Outside Diameter, mm	Wall Thickness, mm	Plain End Mass, kg/m
68	68.000	1.000		...				25.40	1065.89
68	68.000	1.062	716.23	...	...	1700	1727	26.97	1130.73
68	68.000	1.125	759.93	...	...	1700	1727	28.58	1197.09
68	68.000	1.188	804.26	...	...	1700	1727	30.18	1262.92
68	68.000	1.250	848.49	...	...	1700	1727	31.75	1327.39
			891.95	...	...	1700	1727		
72	72.000	0.500		...				12.70	568.87
72	72.000	0.562	382.17	...	...	1800	1829	14.27	638.64
72	72.000	0.625	429.18	...	...	1800	1829	15.88	710.06
72	72.000	0.688	476.87	...	...	1800	1829	17.48	780.92
72	72.000	0.750	524.48	...	...	1800	1829	19.05	850.32
72	72.000	0.812	571.25	...	...	1800	1829	20.62	919.60
72	72.000	0.875	617.93	...	...	1800	1829	22.23	990.52
72	72.000	0.938	665.29	...	...	1800	1829	23.83	1060.87
72	72.000	1.000	712.55	...	...	1800	1829	25.40	1129.78
72	72.000	1.062	758.99	...	...	1800	1829	26.97	1198.57
72	72.000	1.125	805.34	...	...	1800	1829	28.58	1268.98
72	72.000	1.188	852.36	...	...	1800	1829	30.18	1338.83
72	72.000	1.250	899.29	...	...	1800	1829	31.75	1407.25
			945.40	...	...	1800	1829		
76	76.000	0.500		...				12.70	600.50
76	76.000	0.562	403.55	...	...	1900	1930	14.27	674.18
76	76.000	0.625	453.21	...	...	1900	1930	15.88	749.62
76	76.000	0.688	503.60	...	...	1900	1930	17.48	824.45
76	76.000	0.750	553.90	...	...	1900	1930	19.05	897.77
76	76.000	0.812	603.32	...	...	1900	1930	20.62	970.96
76	76.000	0.875	652.65	...	...	1900	1930	22.23	1045.89
76	76.000	0.938	702.70	...	...	1900	1930	23.83	1120.22
76	76.000	1.000	752.66	...	...	1900	1930	25.40	1193.05
76	76.000	1.062	801.75	...	...	1900	1930	26.97	1265.74
76	76.000	1.125	850.75	...	...	1900	1930	28.58	1340.17
76	76.000	1.188	900.47	...	...	1900	1930	30.18	1414.01
76	76.000	1.250	950.09	...	...	1900	1930	31.75	1486.33
			998.85	...	...	1900	1930		
80	80.000	0.562		...				14.27	710.08
80	80.000	0.625	477.25	...	...	2000	2032	15.88	789.56
80	80.000	0.688	530.32	...	...	2000	2032	17.48	868.43
80	80.000	0.750	583.32	...	...	2000	2032	19.05	945.69
80	80.000	0.812	635.39	...	...	2000	2032	20.62	1022.83
80	80.000	0.875	687.37	...	...	2000	2032	22.23	1101.81
80	80.000	0.938	740.12	...	...	2000	2032	23.83	1180.17
80	80.000	1.000	792.77	...	...	2000	2032	25.40	1256.94
80	80.000	1.062	844.51	...	...	2000	2032	26.97	1333.59
80	80.000	1.125	896.17	...	...	2000	2032	28.58	1412.06
80	80.000	1.188	948.57	...	...	2000	2032	30.18	1489.92
80	80.000	1.250	1,000.89	...	...	2000	2032	31.75	1566.20
			1,052.30	...	...	2000	2032		

NOTES:

(1) NPS (Nominal Pipe Size) is a dimensionless designator that has been substituted in the customary units section for the previous term *Inch Nominal Size*.

(2) DN (Nominal Diameter) is a dimensionless designator used in the SI (metric) system to describe pipe size.

B32 AMERICAN NATIONAL STANDARDS FOR PRODUCT SIZES

Preferred Metric Sizes for Flat, Round, Square, Rectangular, and Hexagonal Metal Products B32.100-2005
Welded and Seamless Wrought Steel Pipe B36.10M-2015
Stainless Steel Pipe B36.19M-2004(R2015) *The ASME Publications Catalog shows a complete list of all the Standards published by the Society. For a complimentary catalog, or the latest information about our publications, call 1-800-THE-ASME (1-800-843-2763).*

304L Stainless Steel Pipe

super duplex 2507 pipe

316L stainless steel pipe

duplex 2205 pipe

INTENTIONALLY LEFT BLANK

ASME B36.10M-2015

ISBN 978-0-7918-7027-3



9 780791 870273



M03115